

NORYL™ RESIN GFN1

REGION EUROPE

DESCRIPTION

NORYL™ GFN1 resin is a 10% glass reinforced blend of polyphenylene ether (PPE) + high impact polystyrene (HIPS). This general-purpose injection moldable grade exhibits very low moisture absorption, high strength, hydrolytic stability, Low warpage, low specific gravity, and dimensional stability. NORYL GFN1 carries a UL746C outdoor suitability rating of F1 and is an excellent candidate for a variety of indoor and outdoor applications including construction, electrical components + displays, lawn and garden equipment. *See NORYL GFN1F resin for FDA food compliant / NSF version.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Taber Abrasion, CS-17, 1 kg	50	mg/1000cy	SABIC method
Tensile Stress, yield, 5 mm/min	50	MPa	ISO 527
Tensile Stress, break, 5 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3	%	ISO 527
Tensile Strain, break, 5 mm/min	4	%	ISO 527
Tensile Modulus, 1 mm/min	4000	MPa	ISO 527
Flexural Stress, break, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	3500	MPa	ISO 178
Ball Indentation Hardness, H358/30	100	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	20	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	20	kJ/m ²	ISO 180/1U
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	25	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	25	kJ/m ²	ISO 179/1eU
THERMAL			
Thermal Conductivity	0.24	W/m·°C	ISO 8302
CTE, 23°C to 80°C, flow	5.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	135	°C	ISO 306
Vicat Softening Temp, Rate B/50	125	°C	ISO 306
Vicat Softening Temp, Rate B/120	130	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	130	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	115	°C	ISO 75/Ae
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.3 – 0.5	%	SABIC method
Density	1.17	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.2	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	8	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.E+15	Ohm-cm	IEC 60093

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.8	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.0005	-	IEC 60250
Dissipation Factor, 1 MHz	0.001	-	IEC 60250
Relative Permittivity, 50/60 Hz	2.8	-	IEC 60250
Hot-Wire Ignition (HWI), PLC 0	≥3	mm	UL 746A
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E45329-236754	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
Glow Wire Flammability Index 750°C, passes at ⁽²⁾	3.2	mm	IEC 60695-2-12
Oxygen Index (LOI)	26	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	100 – 120	°C	
Drying Time	2 – 3	hrs	
Melt Temperature	280 – 300	°C	
Nozzle Temperature	260 – 280	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	260 – 280	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 120	°C	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(2) Value shown here is based on internal measurement.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.